

# Rando® HDZ



# **Description**

Rando® HDZ oils are high-viscosity, high-performance, anti-wear hydraulic oils, formulated specifically to cater to the widely varying operating temperatures in the marine environment. These oils are blended from high-viscosity index lubricating oilstocks and several specially selected additives designed to give robust protection to hydraulic pumps. Rando HDZ meets therequirements of major hydraulic equipment manufacturers for rust and oxidation inhibited hydraulic fluids, as well as for EPor anti-wear hydraulic fluids.

# **Typical Characteristics**

ISO Viscosity Grade	15	22	32	46	68	100
MPID	219300	219383	219301	219302	219303	219304
Kinematic viscosity at 40°C, mm²/s	15.0	22.0	32.0	46.0	68.0	100.0
Kinematic viscosity at 100°C, mm²/s	3.9	5.0	6.3	8.2	11.0	14.2
Density at 15°C, kg/l	0.88	0.95	0.87	0.87	0.88	0.88
Viscosity Index	155	165	151	154	150	139
Pour point, °C	-60	-48	-48	<b>-47</b>	-42	<del>-</del> 36
Flash point, °C	144	188	220	216	222	236
Copper Corrosion, 3h/150°C	1A	1A	1A	1A	1A	1A
Foam Seq. II (after blowing), ml	10	10	10	10	10	10
Foam Seq. II (after 10' standing), ml	0	0	0	0	0	0

# **Recommended Applications**

Rando® HDZ oils are recommended for use in all shipboard hydraulic machinery and specifically for hydraulic equipment used under extreme operating temperatures such as deck machinery. The multi-viscosity feature promotes even and continuouspower transmission over a wide temperature range with a minimum of shudder, and maximum accuracy.

## Rando HDZ Oils Are Approved For:

- Fives Cincinnati (formerly MAG Cincinnati, Cin Machine, Cin Milacron) P-68 (ISO 32), P-70 (ISO 46), P-69 (ISO 68)
- **▼** Besensoni crane (ISO 46)
- **✓ Japan IBUKI** horn (ISO 32)
- ✓ Alfa Laval (ISO 32)
- **✓ Sibre** (ISO 32, 46 & 68)
- **✓ Parker Hannifin (Denison)** HFO (ISO 32, 46, 68)



## **Rando HDZ Oils Meet The Requirements Of:**

- **Arburg** (ISO 46), ASTM D6158, HV (ISO 15, 22, 32, 46, 68, 100)
- ✓ **Bosch Rexroth** former specification RE 90220-01 (ISO 32, 46, 68)
- **US Steel** 127, 136 DIN 51524-3, HVLP (ISO 15, 22, 32, 46, 68, 100)
- ✓ Frank Mohn, Framo hydraulic cargo pumping (ISO 46), ISO 11158 L-HV (ISO 15, 22, 32, 46, 68, 100), JCMAS HK-1 (ISO 32, 46)
- **Turblex** compessor (ISO 46)
- ▼ Rehfuss gear (ISO 15 & 32)
- **Eaton-Vickers** I-286-S, M-2950-S, 35VQ25A (ISO 32, 46, 68)

- **✓ Sauer Bibus** geared pump (ISO 46 & 68)
- **✓ Dieckow** pumps (ISO 46 & 68)
- **✓ Europa** regulateur, governor (ISO 68 & 100)
- **✓ Bremivi** planetary gear (ISO 32)
- **✓ Bremivi** winches (ISO 46)
- Goizper pumps (ISO 32 & 46)
- ✓ Hatlapa deck machinery (ISO 46, 68 & 100)
- Mariner deck machinery (ISO 32 & 46)
- **▼ GEA Westfalia** belt driven purifier (ISO 46)
- Manabe Zoki deck machinery (ISO 46 & 68)
- MarFlex pumps (ISO 32 & 46)

## **Performance Benefits**

# 1. Anti-Wear and EP Properties

Extends the life of hydraulic pump and motor parts in heavy-duty service and helps protect against destructive wear under overload conditions.

# 2. Ultra-High Viscosity Index

Contains a specially selected high shear-stable viscosity index improver, which gives the lubricant a superior operating temperature window, even under high shear-rate conditions. Rando HDZ oils provide real "crossgrading" benefits and stay in grade, even when subjected to the shearing condition of high-speed, high-pressure hydraulicsystems in severe service.

# **3.Low Pour Point**

Remains liquid at low operating temperatures.

## 4. Oxidation Stability

High oxidation stability helps ensure long life and prevent accumulation of sludge and deposits.

### **5.Corrosion Protection**

Helps protect against rusting of close-fitting hydraulic system parts and prevents the regeneration of abrasive rust and corrosion.

#### 6. Water Resistance

Water-separation characteristics assure speedy removal ofwater from leaks and condensation.

# 7. Foam Resistant

Combined with selected foam inhibitors, resists foaming, thus preventing accumulation of surface foam at high-oil circulation rates.

## 8. Filterability

Rando HDZ oils show good filterability properties even in the presence of water. They passed the AFNOR NFE 48 dryand wet filterability tests.



**Disclaimer**. Data provided in this PDS is based on standard tests under laboratory conditions and is indicative only. Minor variations which do not affect product performance are expected in normal manufacturing. This product should not be used for any purpose other than those expressly set out in this PDS. The user has sole responsibility for verifying that this product is suitable for the user's intended application. Recommendations differ between engine manufacturersso always consult your manual. Neither Chevron nor its subsidiaries make any warranty or representation as to the accuracy or completeness of this PDS and neither Chevron nor its subsidiaries accept liability for any loss or damage suffered as a result of the use of this product other than in accordance with the termsof this PDS. (January 2024)